

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Air-Pro® (PE)	3" (90mm) SDR7	8.0 bar	2 mm	Almost Zero	123 seconds	8 seconds	8.0 bar	12.3 min
Air-Pro® (PE)	4" (110mm) SDR7	12.0 bar	2 mm	Almost Zero	151 seconds	9 seconds	12.0 bar	14.8 min
Air-Pro® (PE)	6" (160mm) SDR11	17.0 bar	2 mm	Almost Zero	146 seconds	9 seconds	17.0 bar	14.2 min
Air-Pro® (PE)	8" (200mm) SDR11	27.0 bar	2 mm	Almost Zero	182 seconds	10 seconds	27.0 bar	17.3 min
Air-Pro® (PE)	10" (250mm) SDR11	42.0 bar	2.5 mm	Almost Zero	227 seconds	11 seconds	42.0 bar	21.2 min
Air-Pro® (PE)	12" (315mm) SDR11	66.0 bar	3 mm	Almost Zero	286 seconds	13 seconds	66.0 bar	26.4 min
Asahitec™ Solid Wall (PP-RCT)	3" (90mm) SDR11	4.0 bar	1 mm	Almost Zero	94 seconds	6 seconds	4.0 bar	8.6 min
Asahitec™ Solid Wall (PP-RCT)	4" (110mm) SDR11	6.0 bar	1 mm	Almost Zero	113 seconds	7 seconds	6.0 bar	10.2 min
Asahitec™ Solid Wall (PP-RCT)	5" (125mm) SDR11	7.0 bar	1 mm	Almost Zero	129 seconds	7 seconds	7.0 bar	11.5 min
Asahitec™ Solid Wall (PP-RCT)	6" (160mm) SDR11	12.0 bar	1 mm	Almost Zero	161 seconds	8 seconds	12.0 bar	14.2 min
Asahitec™ Solid Wall (PP-RCT)	8" (200mm) SDR11	18.0 bar	1 mm	Almost Zero	198 seconds	9 seconds	18.0 bar	17.3 min
Asahitec™ Solid Wall (PP-RCT)	10" (250mm) SDR11	28.0 bar	1.5 mm	Almost Zero	240 seconds	10 seconds	28.0 bar	21.2 min
Asahitec™ Solid Wall (PP-RCT)	12" (315mm) SDR11	44.0 bar	2 mm	Almost Zero	293 seconds	12 seconds	44.0 bar	26.4 min



Please visit the Asahi Weld App at www.asahi-america.com for up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Asahitec™ Solid Wall (PP-RCT)	3" (90mm) SDR7	6.0 bar	1 mm	Almost Zero	138 seconds	7 seconds	6.0 bar	12.3 min
Asahitec™ Solid Wall (PP-RCT)	4" (110mm) SDR7	8.0 bar	1 mm	Almost Zero	166 seconds	8 seconds	8.0 bar	14.7 min
Asahitec™ Solid Wall (PP-RCT)	5" (125mm) SDR7	10.0 bar	1 mm	Almost Zero	187 seconds	8 seconds	10.0 bar	16.4 min
Chem Proline® (PE)	3" (90mm) SDR11	6.0 bar	1.5 mm	Almost Zero	82 seconds	6 seconds	6.0 bar	8.6 min
Chem Proline® (PE)	4" (110mm) SDR11	8.0 bar	1.5 mm	Almost Zero	100 seconds	7 seconds	8.0 bar	10.2 min
Chem Proline® (PE)	6" (160mm) SDR11	17.0 bar	2 mm	Almost Zero	146 seconds	9 seconds	17.0 bar	14.2 min
Chem Proline® (PE)	8" (200mm) SDR11	27.0 bar	2 mm	Almost Zero	182 seconds	10 seconds	27.0 bar	17.3 min
Chem Proline® (PE)	10" (250mm) SDR11	42.0 bar	2.5 mm	Almost Zero	227 seconds	11 seconds	42.0 bar	21.2 min
Chem Proline® (PE)	12" (315mm) SDR11	66.0 bar	3 mm	Almost Zero	286 seconds	13 seconds	66.0 bar	26.4 min
Climatec™ (PP-RCT)	3" (90mm) SDR11	4.0 bar	1 mm	Almost Zero	94 seconds	6 seconds	4.0 bar	8.6 min
Climatec™ (PP-RCT)	4" (110mm) SDR11	6.0 bar	1 mm	Almost Zero	113 seconds	7 seconds	6.0 bar	10.2 min
Climatec™ (PP-RCT)	5" (125mm) SDR11	7.0 bar	1 mm	Almost Zero	129 seconds	7 seconds	7.0 bar	11.5 min
Climatec™ (PP-RCT)	6" (160mm) SDR17	8.0 bar	1 mm	Almost Zero	108 seconds	6 seconds	8.0 bar	9.8 min



Please visit the Asahi Weld App at www.asahi-america.com for up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Climatec™ (PP-RCT)	8" (200mm) SDR17	12.0 bar	1 mm	Almost Zero	134 seconds	7 seconds	12.0 bar	11.9 min
Climatec™ (PP-RCT)	10" (250mm) SDR17	19.0 bar	1 mm	Almost Zero	163 seconds	8 seconds	19.0 bar	14.4 min
Climatec™ (PP-RCT)	12" (315mm) SDR17	30.0 bar	1 mm	Almost Zero	203 seconds	9 seconds	30.0 bar	17.8 min
Proline® PRO150 (PP)	3" (90mm) SDR11	4.0 bar	1 mm	Almost Zero	94 seconds	6 seconds	4.0 bar	8.6 min
Proline® PRO150 (PP)	4" (110mm) SDR11	6.0 bar	1 mm	Almost Zero	113 seconds	7 seconds	6.0 bar	10.2 min
Proline® PRO150 (PP)	4-1/2" (125mm) SDR11	7.0 bar	1 mm	Almost Zero	129 seconds	7 seconds	7.0 bar	11.5 min
Proline® PRO150 (PP)	5" (140mm) SDR11	9.0 bar	1 mm	Almost Zero	142 seconds	7 seconds	9.0 bar	12.6 min
Proline® PRO150 (PP)	6" (160mm) SDR11	12.0 bar	1 mm	Almost Zero	161 seconds	8 seconds	12.0 bar	14.2 min
Proline® PRO150 (PP)	7" (180mm) SDR11	15.0 bar	1 mm	Almost Zero	180 seconds	8 seconds	15.0 bar	15.8 min
Proline® PRO150 (PP)	8" (200mm) SDR11	18.0 bar	1 mm	Almost Zero	198 seconds	9 seconds	18.0 bar	17.3 min
Proline® PRO150 (PP)	9" (225mm) SDR11	23.0 bar	1.5 mm	Almost Zero	220 seconds	9 seconds	23.0 bar	19.3 min
Proline® PRO150 (PP)	10" (250mm) SDR11	28.0 bar	1.5 mm	Almost Zero	240 seconds	10 seconds	28.0 bar	21.2 min
Proline® PRO150 (PP)	11" (280mm) SDR11	35.0 bar	1.5 mm	Almost Zero	265 seconds	11 seconds	35.0 bar	23.5 min



Please visit the Asahi Weld App at www.asahi-america.com for up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Proline® PRO150 (PP)	12" (315mm) SDR11	44.0 bar	2 mm	Almost Zero	293 seconds	12 seconds	44.0 bar	26.4 min
Proline® PRO90 (PP)	3" (90mm) SDR17.6	3.0 bar	0.5 mm	Almost Zero	60 seconds	5 seconds	3.0 bar	5.4 min
Proline® PRO90 (PP)	4" (110mm) SDR17.6	4.0 bar	0.5 mm	Almost Zero	73 seconds	6 seconds	4.0 bar	6.5 min
Proline® PRO90 (PP)	4-1/2" (125mm) SDR17.6	5.0 bar	1 mm	Almost Zero	82 seconds	6 seconds	5.0 bar	7.4 min
Proline® PRO90 (PP)	5" (140mm) SDR17.6	6.0 bar	1 mm	Almost Zero	92 seconds	6 seconds	6.0 bar	8.2 min
Proline® PRO90 (PP)	6" (160mm) SDR17.6	8.0 bar	1 mm	Almost Zero	104 seconds	6 seconds	8.0 bar	9.2 min
Proline® PRO90 (PP)	7" (180mm) SDR17.6	10.0 bar	1 mm	Almost Zero	116 seconds	7 seconds	10.0 bar	10.2 min
Proline® PRO90 (PP)	8" (200mm) SDR17.6	12.0 bar	1 mm	Almost Zero	129 seconds	7 seconds	12.0 bar	11.3 min
Proline® PRO90 (PP)	9" (225mm) SDR17.6	15.0 bar	1 mm	Almost Zero	143 seconds	7 seconds	15.0 bar	12.4 min
Proline® PRO90 (PP)	10" (250mm) SDR17.6	18.0 bar	1 mm	Almost Zero	157 seconds	8 seconds	18.0 bar	13.5 min
Proline® PRO90 (PP)	11" (280mm) SDR17.6	23.0 bar	1 mm	Almost Zero	175 seconds	8 seconds	23.0 bar	15.2 min
Proline® PRO90 (PP)	12" (315mm) SDR17.6	29.0 bar	1 mm	Almost Zero	195 seconds	9 seconds	29.0 bar	17.0 min
Proline® PRO90 (PP)	14" (355mm) SDR17.6	36.0 bar	1.5 mm	Almost Zero	201 seconds	10 seconds	36.0 bar	18.6 min



Please visit the Asahi Weld App at www.asahi-america.com for up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Proline® PRO45 (PP)	4" (110mm) SDR33	2.0 bar	0.5 mm	Almost Zero	40 seconds	5 seconds	2.0 bar	5.0 min
Proline® PRO45 (PP)	4-1/2" (125mm) SDR33	3.0 bar	0.5 mm	Almost Zero	46 seconds	5 seconds	3.0 bar	5.0 min
Proline® PRO45 (PP)	5" (140mm) SDR33	4.0 bar	0.5 mm	Almost Zero	51 seconds	5 seconds	4.0 bar	5.0 min
Proline® PRO45 (PP)	6" (160mm) SDR33	5.0 bar	0.5 mm	Almost Zero	57 seconds	5 seconds	5.0 bar	5.4 min
Proline® PRO45 (PP)	7" (180mm) SDR33	6.0 bar	0.5 mm	Almost Zero	64 seconds	5 seconds	6.0 bar	6.0 min
Proline® PRO45 (PP)	8" (200mm) SDR33	7.0 bar	0.5 mm	Almost Zero	72 seconds	6 seconds	7.0 bar	6.7 min
Proline® PRO45 (PP)	9" (225mm) SDR33	9.0 bar	0.5 mm	Almost Zero	80 seconds	6 seconds	9.0 bar	7.4 min
Proline® PRO45 (PP)	10" (250mm) SDR33	10.0 bar	1 mm	Almost Zero	89 seconds	6 seconds	10.0 bar	8.1 min
Proline® PRO45 (PP)	11" (280mm) SDR33	13.0 bar	1 mm	Almost Zero	98 seconds	6 seconds	13.0 bar	8.9 min
Proline® PRO45 (PP)	12" (315mm) SDR33	16.0 bar	1 mm	Almost Zero	110 seconds	7 seconds	16.0 bar	9.9 min
Super Proline® (PVDF)	3" (90mm) SDR21	2.0 bar	0.5 mm	Almost Zero	83 seconds	3 seconds	2.0 bar	7.0 min
Super Proline® (PVDF)	4" (110mm) SDR21	3.0 bar	0.5 mm	Almost Zero	93 seconds	3 seconds	3.0 bar	8.5 min
Super Proline® (PVDF)	6" (160mm) SDR21	7.0 bar	0.7 mm	Almost Zero	117 seconds	4 seconds	7.0 bar	11.0 min



Please visit the Asahi Weld App at www.asahi-america.com for up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Super Proline® (PVDF)	8" (200mm) SDR21	10.0 bar	1 mm	Almost Zero	136 seconds	4 seconds	10.0 bar	13.5 min
Super Proline® (PVDF)	10" (250mm) SDR21	16.0 bar	1.1 mm	Almost Zero	159 seconds	4 seconds	16.0 bar	16.5 min
Super Proline® (PVDF)	3" (90mm) SDR33	2.0 bar	0.5 mm	Almost Zero	68 seconds	3 seconds	2.0 bar	5.5 min
Super Proline® (PVDF)	4" (110mm) SDR33	2.0 bar	0.5 mm	Almost Zero	74 seconds	3 seconds	2.0 bar	6.0 min
Super Proline® (PVDF)	6" (160mm) SDR33	5.0 bar	0.5 mm	Almost Zero	89 seconds	3 seconds	5.0 bar	8.0 min
Super Proline® (PVDF)	8" (200mm) SDR33	7.0 bar	0.6 mm	Almost Zero	102 seconds	4 seconds	7.0 bar	9.5 min
Super Proline® (PVDF)	10" (250mm) SDR33	10.0 bar	0.7 mm	Almost Zero	117 seconds	4 seconds	10.0 bar	11.0 min
Super Proline® (PVDF)	12" (315mm) SDR33	16.0 bar	1 mm	Almost Zero	137 seconds	4 seconds	16.0 bar	13.5 min
Watertec™ (PP-RCT)	3" (90mm) SDR9	5.0 bar	1 mm	Almost Zero	114 seconds	7 seconds	5.0 bar	10.3 min
Watertec™ (PP-RCT)	4" (110mm) SDR9	7.0 bar	1 mm	Almost Zero	138 seconds	7 seconds	7.0 bar	12.3 min
Watertec™ (PP-RCT)	5" (125mm) SDR9	9.0 bar	1 mm	Almost Zero	155 seconds	8 seconds	9.0 bar	13.7 min
Watertec™ (PP-RCT)	6" (160mm) SDR11	12.0 bar	1 mm	Almost Zero	161 seconds	8 seconds	12.0 bar	14.2 min
Watertec™ (PP-RCT)	8" (200mm) SDR11	18.0 bar	1 mm	Almost Zero	198 seconds	9 seconds	18.0 bar	17.3 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Watertec™ (PP-RCT)	10" (250mm) SDR11	28.0 bar	1.5 mm	Almost Zero	240 seconds	10 seconds	28.0 bar	21.2 min
Watertec™ (PP-RCT)	12" (315mm) SDR11	44.0 bar	2 mm	Almost Zero	293 seconds	12 seconds	44.0 bar	26.4 min
Fluidlok (IPS) (PE)	3" X 6" SDR11X17	12.0 bar	mm	Almost Zero	65 seconds	5 seconds	12.0 bar	10.0 min
Fluidlok (IPS) (PE)	4" X 8" SDR11X17	21.0 bar	mm	Almost Zero	86 seconds	5 seconds	21.0 bar	12.0 min
Fluidlok (IPS) (PE)	6" X 10" SDR11X17	35.0 bar	mm	Almost Zero	105 seconds	6 seconds	35.0 bar	14.0 min
Poly-Flo® PE100RC (PE)	4" X 6" (110mm X 160mm) SDR11X17	16.8 bar	1.5 mm	Almost Zero	80 seconds	7 seconds	16.8 bar	14.0 min
Poly-Flo® PPR (PP)	4" X 6" (110mm X 160mm) SDR11X17	13.9 bar	1 mm	Almost Zero	150 seconds	7 seconds	13.9 bar	17.0 min
Duo-Pro® PRO150X150 (PP)	3" X 6" (90mm X 160mm) SDR11X11	16.0 bar	1 mm	Almost Zero	161 seconds	8 seconds	16.0 bar	14.2 min
Duo-Pro® PRO150X150 (PP)	4" X 8" (110mm X 200mm) SDR11X11	24.0 bar	1 mm	Almost Zero	198 seconds	9 seconds	24.0 bar	17.3 min
Duo-Pro® PRO150X150 (PP)	6" X 10" (160mm X 250mm) SDR11X11	40.0 bar	1.5 mm	Almost Zero	240 seconds	10 seconds	40.0 bar	21.2 min
Duo-Pro® PRO150X150 (PP)	2" X 6" (63mm X 160mm) SDR11X11	14.1 bar	1 mm	Almost Zero	161 seconds	8 seconds	14.1 bar	14.2 min
Duo-Pro® PRO150X45 (PP)	3" X 6" (90mm X 160mm) SDR11X33	9.0 bar	0.5 mm	Almost Zero	94 seconds	6 seconds	9.0 bar	8.6 min
Duo-Pro® PRO150X45 (PP)	4" X 8" (110mm X 200mm) SDR11X33	13.0 bar	0.5 mm	Almost Zero	113 seconds	7 seconds	13.0 bar	10.2 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Field 12 (Butt) Welding Parameters

CURRENT AS OF
04/11/2023

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Duo-Pro® PRO150X45 (PP)	6" X 10" (160mm X 250mm) SDR11X33	22.0 bar	1 mm	Almost Zero	161 seconds	8 seconds	22.0 bar	14.2 min
Duo-Pro® PRO150X45 (PP)	8" X 12" (200mm X 315mm) SDR11X33	34.0 bar	1 mm	Almost Zero	198 seconds	9 seconds	34.0 bar	17.3 min
Duo-Pro® PRO150X45 (PP)	2" X 6" (63mm X 160mm) SDR11X33	7.1 bar	0.5 mm	Almost Zero	68 seconds	6 seconds	7.1 bar	6.3 min
Duo-Pro® PRO45X45 (PP)	4" X 8" (110mm X 200mm) SDR33X33	9.0 bar	0.5 mm	Almost Zero	72 seconds	6 seconds	9.0 bar	6.7 min
Duo-Pro® PRO45X45 (PP)	6" X 10" (160mm X 250mm) SDR33X33	15.0 bar	1 mm	Almost Zero	89 seconds	6 seconds	15.0 bar	8.1 min
Duo-Pro® PRO45X45 (PP)	8" X 12" (200mm X 315mm) SDR33X33	23.0 bar	1 mm	Almost Zero	110 seconds	7 seconds	23.0 bar	9.9 min
Duo-Pro® PVDFXPVDF (PVDF)	6" X 10" (160mm X 250mm) SDR33X33	15.0 bar	0.7 mm	Almost Zero	117 seconds	4 seconds	15.0 bar	11.0 min
Duo-Pro® PVDFXPVDF (PVDF)	2" X 6" (63mm X 160mm) SDR21X33	6.3 bar	0.5 mm	Almost Zero	89 seconds	3 seconds	6.3 bar	8.0 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint